



Report No. 392-2013-00053902_EN

Akemi Chemisch Technische Spezialfabrik GmbH Lechstraße 28 90451 Nürnberg Germany Eurofins Product Testing A/S Smedeskovvej 38 8464 Galten Denmark

voc@eurofins.com www.eurofins.com/voc-testing

Date 19 March 2014

VOC Emissions Test report

1. Sample Information

Sample identification	Anti-Fleck Nano Effect
Product type	Paint
Batch no.	2818313
Production date	KW 31 2013
Date when sample was received	27/08/2013
Testing (start - end)	29/08/2013 - 26/09/2013

2. Resulting VOC Emissions Class Label

This recommendation is based on French regulation of March 23, 2011 (décret DEVL1101903D) and of April 19, 2011 (arrêté DEVL1104875A). For details please see www.eurofins.com/france-voc



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

The product was assigned a VOC emission class without taking into account the measurement uncertainty associated with the result. As specified in French Decree no. 2011-321 of March 23, 2011, correct assignment of the VOC emission class is the sole responsibility of the party responsible for distribution of the product in the French market.

3. Conclusion on CMR emissions

The tested product fulfills the requirements of the French regulation DEVP0908633A of 30 April 2009 and DEVP0910046A of 28 May 2009. For details please see www.eurofins.com/france-voc.





Report No. 392-2013-00053902_EN

4. Test Method

Method		Principle	Parameter		Quantification limit	Uncer	tainty			
ISO 16000 parts -3, -6, -9, -11		GC/MS	VOC		2 μg/m³					
Internal method numbers: 9810, 9811, 9812, 2808, 8400		HPLC/UV	Volatile alde- hydes		3 μg/m³	22% (RSD)				
ISO 16000 parts -3, -6, -9, -11		HPLC/UV	4CMR		<1 µg/m³	Um = 2 x				
Internal method numbers: 9810, 9811, 9812, 2808, 8400, 2616						RSD=45 %				
Test chamber parameter	,									
Chamber volume, I	119	Temperature, °C		23±1	Relative humidity, %		50±5			
Air change rate, 1/h	0.5	Loading ratio, m²/m³ 0.4								
Test condition: Sample stayed in test chamber during the whole 28 days testing period.										
Sample preparation										
Application amount, g/m²	156	Number of layers		1	Drying time, h		_			





Report No. 392-2013-00053902_EN

5. Results

	Concentration after 28 days µg/m³	С	В	Α	A+			
TVOC	46	>2000	<2000	<1500	<1000			
Formaldehyde	<3	>120	<120	<60	<10			
Acetaldehyde	<3	>400	<400	<300	<200			
Toluene	<2	>600	<600	<450	<300			
Tetrachloroethylene	<2	>500	<500	<350	<250			
Ethylbenzene	<2	>1500	<1500	<1000	<750			
Xylene	<2	>400	<400	<300	<200			
Styrene	<2	>500	<500	<350	<250			
2-Butoxyethanol	<2	>2000	<2000	<1500	<1000			
1,2,4- Trimethylbenzene	<2	>2000	<2000	<1500	<1000			
1,4-Dichlorobenzene	<2	>120	<120	<90	<60			
CMR compounds		Maximum allowed air concentration						
Benzene	<1	<1						
Trichloroethylene	<1	<1						
Dibutylphthalate (DBP) *	<1	<1						
Diethylhex- ylphthalate (DEHP) *	<1	<1						

- < Means less than
- > Means higher than
- * Not a part of our accreditation (EN ISO/IEC 17025:2005) by DANAK (no. 522))

Thomas Neuhaus

Head of product emission test centre